

# SE2011

## 2-Part Self bonding potting compound

### Introduction

This is a self-bonding 2-component, silicone elastomer system specially designed for electronic potting and encapsulation applications. It offers good protection against chemicals, environmental contamination, mechanical shock, vibration and impact damage. It can be employed in areas where low flammability is a prerequisite. The cured elastomer can be repaired. The component parts have relatively low viscosities and are readily mixed either by hand or machine.

This silicone elastomer has the benefit of developing chemical adhesion to a variety of substrates and is compatible with many sensitive substrates including copper, brass, steel, aluminium, FR4, and plastics making this an ideal option where fast curing and adhesion are needed without the use of a primer.

### Key Features

- Adhesive at room temperature
- Fast curing at room temperature
- Low viscosity
- UL Listed in file No. E334038

### Use and Cure Information

The product is supplied as two components 'A' and 'B'. These components should be mixed together in the ratio by weight shown opposite. Mixing can be done by hand or by automated dispensing machine using a static mixer nozzle. A nozzle of at least 9 GXF type elements is recommended for uniform mixing of both components.

The dispensing machine mix ratios should be adjusted if mixing by volume and not weight. **IMPORTANT** the mixed components will cure in the nozzle so to preserve nozzles a continuous process is required or a change of nozzle after the task is completed. Complete mixing of each component is achieved within the first 50-60% of the nozzle.

### Mixing

Both the 'A' and 'B' parts should be well stirred to ensure the material is uniform and any settlement of the fillers have been remixed.

Place the required amount of 'A' and 'B' parts by weight at the mix ratio shown opposite, in a clean plastic or metal container of approximately 3 times their volume, and mix until the colour of the mixture is uniform. For best results, we recommend degassing. Degass by intermittent evacuation, the larger volume of the mixing vessel helps prevent overflow during this operation. In case of automatic dispensing with static mixing head, the two components should be degassed before processing. Recommended vacuum conditions are 30-50 mbar intermittently over 5-10 minutes. Cast the mixture either by gravity or pressure injection.

Complete mixing of each component is achieved within the first 50-60% of the nozzle.

### Adhesion

Ensure all substrates are clean and free of surface contaminants. A Solvent degreaser is recommended for metallic substrates and Iso-propanol solvent is recommended for plastics and polycarbonates. A mechanical bond to the substrates will develop shortly after applying. A chemical bond will develop after 24 hours and maximum adhesion is reached after 7 days.

### Health and Safety

Safety Data Sheets available on request.

### Packaging

ACC Encapsulants are available in a variety packaging including bulk containers. Please contact our sales department for more information.

Revision Date : 02/11/2017

Download Date : 25/07/2018

### Property

#### Uncured product

Property	Test Method	Value
Appearance		<b>Black liquid</b>
Colour A Part		<b>Black</b>
Colour B Part		<b>Clear</b>
Cure Type		<b>Condensation</b>
Max Cure Hrs @ 25 °C		<b>2 hrs</b>
Mix Ratio		<b>10:1</b>
Pot Life mins		<b>20 mins</b>
Rheology		<b>Liquid</b>
Self Bonding		<b>Yes</b>
Viscosity A-Part mPas	Brookfield	<b>4400 mPas</b>
Viscosity B-Part mPas	Brookfield	<b>100 mPas</b>
Viscosity Mixed mPas	Brookfield	<b>4000 mPas</b>

#### Cured product

**After 7 days cure at 23° +/- 2°C and 50+/- 5% humidity**

CTE Linear ppm/°C		<b>279 ppm/°C</b>
CTE Volumetric ppm/°C		<b>837 ppm/°C</b>
Colour		<b>Black</b>
Duro Shore A	ASTM D 2240-95	<b>23</b>
Elongation %	ISO 37	<b>270 %</b>
Max Working Temp +°C	AFS_1540B	<b>220 °C</b>
Min Working Temp - °C		<b>-50 °C</b>
SG	BS ISO 2781	<b>1.08</b>
Tensile MPa	ISO 37	<b>0.9 MPa</b>
Thermal Conductivity W/mK		<b>0.2 W/mK</b>

#### Storage

Max storage temperature °C	<b>40 °C</b>
Shelf life	<b>6 mths</b>

#### Electrical properties

Dielectric Constant @ 1kHz	ASTM D-150	<b>3.28</b>
Dissipation Factor @ 1kHz	ASTM D-150	<b>0.029</b>
Volume Resistivity ohms cm	ASTM D-257	<b>1.09E+14 ohms cm</b>

The information and recommendations in this publication are to the best of our knowledge reliable. However nothing herein is to be construed as warranty or representation. Users should make their own test to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the user of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.