

DELO KATIOBOND 45952

modified epoxy resin | 1C | light-activated

free of solvents | unfilled, thixotropic | preactivated

Special features of product

- halogen-free according to IEC 61249-2-21
- compliant with RoHS Directive 2015/863/EU
- passes ANSI/UL 94 HB Flame Test

Typical area of use

- -40 - 150 °C

Curing

Suitable lamp types LED 365 nm, LED 400 nm,
LED 460 nm, UVA

Processing

Adhesive application needle-dispensable, jettable

Storage life in unopened original container as from production date

at 0 °C to +25 °C 6 month(s)

Technical properties

Color in cured condition in 0.1 mm layer thickness yellow

Transparency in cured condition in 0.1 mm layer thickness transparent

Fluorescence fluorescent

Parameters

Density 1.15 g/cm³
Based on DIN EN ISO 2811-3 | Liquid

Viscosity 6300 mPa·s
Liquid | Rheometer | Shear rate: 10 1/s

Thixotropy index 2.8
Liquid | Rheometer

Preactivation time for defined open time <i>DELO Standard 19 Cardboard 460 nm 200 mW/cm²</i>	8	s
Open time after preactivation <i>DELO Standard 19 Cardboard 460 nm 200 mW/cm²</i>	≤ 18	s
Maximum layer thickness that can be preactivated <i>DELO Standard 21 460 nm 200 mW/cm² 8 s Plus 24 h</i>	≥ 4	
Compression shear strength <i>DELO Standard 5 PMMA PMMA 460 nm 200 mW/cm² 9 s Plus 24 h</i>	9	MPa
Compression shear strength <i>DELO Standard 5 PC PC 400 nm 200 mW/cm² 60 s Plus 24 h</i>	15	MPa
Compression shear strength <i>DELO Standard 5 PC Al 400 nm 200 mW/cm² 60 s Plus 24 h</i>	10	MPa
Compression shear strength <i>DELO Standard 5 Glass FR4 400 nm 200 mW/cm² 60 s Plus 24 h</i>	20	MPa
Compression shear strength <i>DELO Standard 5 Glass LCP E130i 400 nm 200 mW/cm² 60 s Plus 24 h</i>	6	MPa
Compression shear strength <i>DELO Standard 5 Glass Glass 400 nm 200 mW/cm² 60 s Plus 24 h</i>	20	MPa
Compression shear strength <i>DELO Standard 5 Glass PBT 400 nm 200 mW/cm² 60 s Plus 24 h</i>	7	MPa
Compression shear strength <i>DELO Standard 5 Glass Al 400 nm 200 mW/cm² 60 s Plus 24 h</i>	20	MPa
Tensile strength <i>Based on DIN EN ISO 527 400 nm 200 mW/cm² 60 s Plus 24 h</i>	30	MPa
Elongation at tear <i>Based on DIN EN ISO 527 400 nm 200 mW/cm² 60 s Plus 24 h</i>	85	%
Young's modulus <i>DMTA 400 nm 200 mW/cm² 60 s Plus 24 h Type of storage: Temp. Temp.: 205 °C Duration: 30 min</i>	1100	MPa
Shore hardness D <i>Based on DIN EN ISO 868 400 nm 200 mW/cm² 60 s Plus 24 h</i>	67	

Glass transition temperature <i>DMTA 400 nm 200 mW/cm² 60 s Plus 24 h Type of storage: Temp. Temp.: 205 °C Duration: 30 min</i>	39	°C
Coefficient of linear expansion <i>DELO Standard 26 TMA Evaluation T: 30 °C - 145 °C 400 nm 200 mW/cm² 60 s Plus 24 h</i>	200	ppm/K
Shrinkage <i>DELO Standard 13 400 nm 200 mW/cm² 60 s Plus 24 h</i>	3.7	vol. %
Water absorption <i>Based on DIN EN ISO 62 400 nm 200 mW/cm² 60 s Plus 24 h Type of storage: Desiccator Duration: 72 h</i>	2.1	wt. %
Decomposition temperature <i>DELO Standard 36</i>	220	°C

Converting table

°F = (°C x 1.8) + 32	1 MPa = 145.04 psi
1 inch = 25.4 mm	1 GPa = 145.04 ksi
1 mil = 25.4 µm	1 cP = 1 mPa·s
1 oz = 28.3495 g	1 N = 0.225 lb

General curing and processing information

The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value. Increasing or decreasing the curing temperature and / or irradiation intensity shortens or prolongs the curing time and can lead to changed physical properties.

A short irradiation time (preactivation time) results in an open time within which opaque components can be joined.

The cationic curing mechanism enables the adhesive to cure on opaque components after joining by sufficient preactivation.

All curing or light fixation parameters depend on material thickness and absorption, adhesive layer thickness, lamp type and distance between lamp and adhesive layer.

Curing until final strength proceeds within 24 hours at room temperature.

Values measured after 24 h at approx. 23 °C / 50 % r.h., unless otherwise specified.

General

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or

the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

Instructions for use

The instructions for use are available on www.DELO-adhesives.com.

We will be pleased to send them to you on demand.

Occupational health and safety

See material safety data sheet.

Specification

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

CONTACT