

DELO MONOPOX GE727

modified epoxy resin | 1C | heat-curing

free of solvents | filled | low CTE, flowable

Special features of product

- compliant with RoHS Directive 2015/863/EU
- halogen-free according to IEC 61249-2-21

Function

- electronic encapsulant
- Fill for Dam&Fill

Typical area of use

- -65 - 180 °C
- encapsulation of chip modules
- large-area encapsulation and potting

Curing

Recommended curing time

at +150 °C in air convection oven	20	min
at +120 °C in air convection oven	90	min

Processing

Conditioning time (typical)

when stored in cold conditions in containers up to 10 ml	0.5	h
when stored in cold conditions in containers up to 50 ml	1	h

Processing time

in standard climate +23 °C / 50 % r. h.	24	h
---	----	---

Storage life in unopened original container

at -40 °C	6	month(s)
-----------	---	----------

Technical properties

Color in cured condition in 1 mm layer thickness	black	
Transparency in cured condition in 1 mm layer thickness	opaque	
Filler particle type	minerals	
Filler particle size	d95 = 65 µm	
Filler content	80	wt. %

Parameters

Density <i>DELO Standard 13 Liquid</i>	1.85	g/cm ³
Viscosity <i>Liquid Rheometer Shear rate: 10 1/s</i>	18000	mPa·s
Compression shear strength <i>DELO Standard 5 PBT PBT 150 °C 20 min</i>	5	MPa
Compression shear strength <i>DELO Standard 5 PPS PPS 150 °C 20 min</i>	25	MPa
Compression shear strength <i>DELO Standard 5 AI AI 150 °C 20 min</i>	15	MPa
Compression shear strength <i>DELO Standard 5 FR4 FR4 150 °C 20 min</i>	54	MPa
Compression shear strength <i>DELO Standard 5 LCP T130 LCP T130 150 °C 20 min</i>	9	MPa
Compression shear strength <i>DELO Standard 5 PA6 PA6 150 °C 20 min</i>	5	MPa
Tensile strength <i>Based on DIN EN ISO 527 150 °C 20 min</i>	59	MPa
Elongation at tear <i>Based on DIN EN ISO 527 150 °C 20 min</i>	0.5	%

Young's modulus	12300	MPa
-----------------	-------	-----

Based on DIN EN ISO 527 / 150 °C / 20 min

Shore hardness D	87	
------------------	----	--

Based on DIN EN ISO 868 / 150 °C / 20 min

Glass transition temperature	165	°C
------------------------------	-----	----

DSC

Coefficient of linear expansion	43	ppm/K
---------------------------------	----	-------

DELO Standard 26 / TMA / Evaluation T: 155 °C - 230 °C / 150 °C / 20 min

Coefficient of linear expansion	11	ppm/K
---------------------------------	----	-------

DELO Standard 26 / TMA / Evaluation T: 30 °C - 135 °C / 150 °C / 20 min

Shrinkage	1.2	vol. %
-----------	-----	--------

DELO Standard 13 / 150 °C / 20 min

Water absorption	0.1	wt. %
------------------	-----	-------

Based on DIN EN ISO 62 / 150 °C / 20 min / Type of storage: Media / Medium: Distilled water / Temp.: at approx. +23 °C

Decomposition temperature	318	°C
---------------------------	-----	----

DELO Standard 36

Extractable chloride ions	<10	ppm
---------------------------	-----	-----

150 °C / 20 min

Extractable potassium ions	<10	ppm
----------------------------	-----	-----

150 °C / 20 min

Extractable sodium ions	<10	ppm
-------------------------	-----	-----

150 °C / 20 min

Converting table

°F = (°C x 1.8) + 32	1 MPa = 145.04 psi
1 inch = 25.4 mm	1 GPa = 145.04 ksi
1 mil = 25.4 µm	1 cP = 1 mPa·s
1 oz = 28.3495 g	1 N = 0.225 lb

General curing and processing information

The curing time stated in the technical data was determined in the laboratory. It can vary depending on the adhesive quantity and component geometry and is therefore a reference value.

The heating time of the components must be added to the actual curing time. It depends on component size

and oven type. The specified curing temperature must be reached directly at the adhesive. Increasing or decreasing the curing temperature and / or irradiation intensity shortens or prolongs the curing time and can lead to changed physical properties. Depending on the adhesive quantity used, exothermic reaction heat is generated which can lead to overheating. In this case, a lower curing temperature is to be selected. Values measured after 24 h at approx. 23 °C / 50 % r.h., unless otherwise specified.

General

The data and information provided are based on tests performed under laboratory conditions. Reliable information about the behavior of the product under practical conditions and its suitability for a specific purpose cannot be concluded from this. It is the customer's responsibility to test the suitability of a product for the intended purpose by considering all specific requirements and by applying standards the customer deems suitable (e. g. DIN 2304-1). Type, physical and chemical properties of the materials to be processed with the product, as well as all actual influences occurring during transport, storage, processing and use, may cause deviations in the behavior of the product compared to its behavior under laboratory conditions. All data provided are typical average values or uniquely determined parameters measured under laboratory conditions. The data and information provided are therefore no guarantee for specific product properties or the suitability of the product for a specific purpose.

Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent.

All products provided by DELO are subject to DELO's General Terms of Business. Verbal ancillary agreements are deemed not to exist.

Instructions for use

The instructions for use are available on www.DELO-adhesives.com.

We will be pleased to send them to you on demand.

Occupational health and safety

See material safety data sheet.

Specification

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. This Technical Datasheet is for reference only and does not constitute a product specification. Please ask our responsible Sales Engineer for the applicable product specification which includes defined ranges. DELO is neither liable for any values and content of this Technical Datasheet nor for oral or written recommendations regarding the use, unless otherwise agreed in writing. This limitation of liability is not applicable for damages resulting from intent, gross negligence or culpable breach of cardinal obligations, nor shall it apply in case of death or personal injury or in case of liability under any applicable compulsory law.

CONTACT

DELO MONOPOX GE727 | as of 11.02.2020 09:38 | Page 4 of 4

DELO Industrial Adhesives
Headquarters

► Germany · Windach / Munich ... www.DELO-adhesives.com

ADHESIVES

DISPENSING

CURING

CONSULTING

DELO